



Specs: 26.17Specs20

**Treatment of walls around
Windows and Doors, Parapets, etc.
Areas of Rising Damp – Below
Dampcourse,**

MAXQUICK® ROLL

Products required

- **MAXQUICK ROLL**
- **MAXREST**

Method

1. Prepare area to be treated by removing any loose materials ensuring a clean and sound surface.
2. Any damage to the surface should be repaired using **MAXREST**.
3. Thoroughly wet the entire surface before applying coating. Use **MAXQUICK ROLL** on previously uncoated surfaces. Single coat application.
MAXQUICK ROLL is supplied as a cement powder that mixes with water. This mixture is then brushed onto a pre-dampened (wet) surface.
4. Once coated the surface should be allowed minimum 24 hours before final paint or texture coating is applied.



To prevent flaking, peeling and discolouring of painted surfaces.



Here rising damp is causing paint to blister on the bottom course below the dampcourse.

Maxquick Roll is ideal for use under Morrocca & other acrylic textured coatings and painted finishes or, external cladding to provide a dry surface. DO NOT USE to waterproof areas subject to negative water flow or standing water.